

BETONCORD®/40



Concrete hose

Marking:  Betoncord® Concrete / Beton PN 40 bar

Norm	EN ISO 1307:2008, ISO 4649 (previous DIN 53516)	Compound tube	SBR/NR
Working pressure	40 bar	Abrasion value tube	70 mm ³
Bursting pressure	120 bar	Construction tube	Smooth
Min. temperature	-35 °C	Color tube	Black
Max. temperature	+80 °C	Compound cover	SBR
Electr. resistance tube	Electrical conductive <10 ⁶ Ω	Cover	Fabric finish
Electr. resistance cover	Antistatic <10 ⁹ Ω	Color cover	Black
Eletr. resistance tube to cover	Antistatic <10 ⁹ Ω	Reinforcements	Textile plies

Art.-no.	Ø Inner (mm)	Wall (mm)	Ø Outer (mm)	Bending radius (mm)	Weight (kg/mtr)	Length (mtr)
3520025000	25,0	7,0	39,0	250	0,840	40
3520035000	35,0	7,0	49,0	350	1,150	40
3520038000	38,0	8,0	54,0	380	1,480	40
3520050000	50,0	9,0	68,0	500	1,950	40
3520063000	63,5	11,0	85,5	650	2,920	40

Application: Suitable for concrete mortar and other wet abrasive materials such as grouting mortar, plaster, plaster mortar and others. The hose can also be used for dry substances such as cement and blasting grit. Very long lifespan due to very thick wear resistant tube and cover. The hose is kink-resistant due to the special compact construction of the insertions. This allows the hose to be used at high working pressures.

Remark:

- Cutted length possible

